

(MPa)

γ



Properties and uses:

Highly fire resistant, high chemical resistance and good mechanical characteristic make these gaskets suitable for application in oil and fuel at high temperature. Not suitable with steam.



| Composition | Fluorinated Rubber | Thickness | 1.0 mm, 1.5 mm, 2.0 mm, 3.0 mm. |
|-----------------|--------------------|-----------|------------------------------------|
| Color | Black | | Other thicknesses on request. |
| Constant Tighte | ening | | |

| TECHNICAL DATA – Typical values for a thickness of 2.0 mm |
|---|

0

0,5

| Density | UNI 7092 | g/cm ³ | 1.88 |
|---------------------------|------------|-------------------|------------|
| Temperature (Air) | | °C | -10 / 200 |
| Temperature (Water) | | °C | 100 |
| Temperature (Oil) | | °C | 150 |
| Hardness | UNI 4916 | Shore A | 75 ± 5 |
| Breaking Stress | UNI 6065 | MPa | Min. 7 |
| Ultimate Elongation | UNI 6065 | % | 300 |
| Tear Resistance | UNI 4914 C | N/mm | Min. 20 |
| Ozone Resistance UNI 9185 | | | Lindonagad |
| after 72h at 50°C | 0101 9183 | | Undamaged |
| Ageing in Air | UNI 6067 | | |
| after 72h at 200°C | | | |
| ∆ Hardness | | Shore A | +3 |
| ∆ Breaking Stress | | % | -10 |
| ∆ Ultimate Elongation | | % | -20 |
| Ageing in Oil ASTM 1 | | | |
| ter 72 h at 100 °C | | | |
| ∆ Hardness | | Shore A | -10 |
| Δ Volume | | % | +10 |

The maximum exercise's condition depend on many factor as the gasket's dimension, the clamping value between the flanges, etc

-Is not advised the use in the maximum temperature and at the same time with the maximum pressure.

Since all properties, specifications and application parameters shown throughout this catalogue are approximate and may be mutually influenced, your specific application should not be undertaken without independent study and evaluation for suitability. All technical data and advice given is based on experiences KLINGER Italy has made so far. Failure to select proper sealing products can result in damage and/or personal injury. Properties, specifications and application parameters are subject to change without notice. KLINGER Italy does not undertake any liability of any kind whatsoever. Is not advised the use in the maximum temperature and at the same time with the maxi-mum pressure.